

BEOGRADE FLM048

Material Technical Data Sheet



Date of issue: 25/01/2022 Version: 2.0

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier Product form

Name

Product code

Application

Composition

- Granulate
- Beograde FLM048 9802070048
- : 980207004 : Biodegrada
 - Biodegradable and compostable polymer suitable for blown film applications
- 100% biodegradable compound and additives

1.2. Details of the supplier of the material specification sheet

Manufacturer Beologic Jolainstraat 44 8554 Sint-Denijs

info@beologic.com

SECTION 2: Physical, mechanical and thermal properties 2.1. Information on basic physical, mechanical and thermal properties

Properties⁽¹⁾ Method **Typical Value** Unit **Composition / Physical** Content Complex blend of biopolymers Renewable content ≥ 30 % Colour material White Coloured in mass No Transmission Opaque Physical state Solid Relative density ISO 1183-1 1,2-1,3 g/cm³ UV package No Kg CO₂ Eq/ kg Carbon footprint⁽²⁾ PAS 2050 *5,8793 Shelf life⁽³⁾ 6 Months Mechanical Tensile modulus ISO 527 780 MPa Tensile strength ISO 527 19,2 MPa Ultimate strain ISO 527 11 % Break stress ISO 527 19,1 MPa Elongation at break ISO 527 390 % Flexural modulus 680 MPa ISO 178 Flexural strength ISO 178 22 MPa 76 (Notched 1eA, 23 °C) ISO 179 kJ/m² Charpy impact strength Thermal (190°C, 2.16 kg) MFI ISO 1133-1 3-4 g/10min Melting temperature range ISO 11357-3 120-130 °C Decomposition temperature (TGA) ISO 3451-1 300 °C Ash content (TGA) ISO 3451-1 ≤ 15 %

(1) Typical properties; not to be construed as specifications.

(2) Carbon footprint calculated by Neutrologic

(3) Only if storage conditions were followed
*Our Beograde grades are made carbon neutral by offsetting through certified climate projects.



Date of issue: 25/01/2022 Version: 2.0

2.2. Processing conditions

Hopper	40 - 60	°C
Feeding zone	160 – 165	°C
Compression zone	165 – 165	°C
Metering zone	165 – 170	°C
Die	170 – 175	°C
Blow up rotation	2-4	

If the melt is too viscous, the temperatures can be increased stepwise by 5°C up to a maximum of 200°C melt temperature.

General advice

Beograde is not compatible with a wide variety of other resins, and special purging sequences should be followed:

- 1. Before production, ensure to clean extruder and bring temperature to steady state with low viscosity, general purpose PP or PE.
- 2. Vacuum out hopper system to avoid contamination.
- 3. Introduce Beograde into the extruder at the operating conditions used in step one.
- 4. Once Beograde has purged, reduce barrel temperatures to desired set points.
- 5. At shutdown, purge machine with high viscosity polystyrene or polypropylene.

Purging time: approximately 10 to 20 minutes.

At higher temperature, the dwell time of the material inside the machine shall be reduced to a minimum in order to lower the risk of degradation. Don't leave the material hot inside the machine for long periods as the material will degrade.

2.3. Product Carbon footprint

The product carbon footprint helps to define the amount of greenhouse gas emissions generated by a product along its life cycle, it quantifies the ghg-emissions related to the production of our products.

Beologic calculates the carbon footprint of all sales products and this from cradle to gate.

The calculation of the carbon footprint is in accordance with the internationally recognized Greenhouse Gas Protocol Product Standard which is based on the standard ISO-14067 norm and PAS2050.

The carbon footprint is mentioned in our datasheet - by offsetting or compensating the calculated emissions we can present our products as Carbon Neutral compounds. This compensation is according the Verified Carbon Standard – more info via (www.v-c-s.org).

SECTION 3: Drying conditions and storage

Beograde FLM048 is a compound of biodegradable polymers (such as PLA). Residual moisture content can lead to hydrolysis degradation. **We recommend drying Beograde FLM048 at 60°C for a period of 2 – 4 hours.** Don't overheat or dry it longer than recommended. Residual moisture content (> 0.2%) can result in lower melt stability, surface mark or bubble formation during processing.

We recommend to store the material in dry conditions below 50°C and protected from UV-light. Opened bigbag should be used immediately or adequately sealed back up after use to avoid moisture uptake and have negative effects on the physical properties of the product. It is recommended to use Beograde granules within a time period of maximum 6 months.

Finished product made from Beograde should be stored dry and cold. Storage time and lifetime of finished products depends on processing parameters and on storage conditions (moisture, UV radiation ...).

SECTION 4: Biodegradability and compostability

Beograde FLM048 fulfills the requirements of the existing standards for compostable and biodegradable polymers (EN 13432), because it can be degraded by microorganisms.

As the compostability of the end product is dependent on the geometry of product, it is the responsibility of the manufacturer of the end product to ensure compliance with the regulations.

SECTION 5: Food regulation

Beograde FLM048 complies in its composition with the European food stuff legislation for food contact, EU Directive 10/2011/EC (and the amendments 2018/213 and 2018/831).

The material also complies with the US food contact notification for the main components: e.g. FCN 178, 475 and 907. A detailed food law status can be given on request. Whether the article is suitable for the application, has to be checked by the converter or packer.



BEOGRADE FLM048 Material Technical Data Sheet



Date of issue: 25/01/2022 Version: 2.0

The technical data above are based on our current knowledge and experience. They do not release from the obligation to make one's own evaluation and trials, in respect to a variety of possible influences in processing and application of the product. A legally binding guarantee of certain properties or suitabilities for a special kind of application cannot be derived from the data.