



TotalEnergies

Refining & Chemicals
Polymers

M3583UV Black

Technical data sheet – Issue 2
Polyethylene
Produced in Europe

Description

M3583UV Black is a new generation Medium Density Metallocene Polyethylene with hexene as comonomer. M3583UV Black is intended for the manufacture of rotomolded items and available in black powder.

Its specific molecular structure ensures:

- ✓ Superior mechanical properties
- ✓ Improved dimensional stability
- ✓ Easy processing
- ✓ High ESCR
- ✓ UV protected

Suitable to produce Diesel Fuel Tanks (TÜV ECE R34) & technical parts.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 190°C/2.16 kg	ISO 1133-1	g/10 min	6,0
Mechanical properties			
Tensile strength at yield	ISO 527	MPa	17
Elongation at Break	ISO 527	%	> 700
Flexural Modulus	ISO 178	MPa	700
Thermal properties			
Melting Temperature	internal method	°C	123
Vicat Softening point A50 (10N, 50°C/h)	ISO 306	°C	121
Stress Cracking			
Bell ESCR (10% Igepal)	ASTM D 1693	F50 in hours	> 250
Other physical properties			
Density	ISO 1183	g/cm³	0,937

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery, provided storage conditions are used as given in the SDS of our product. SDS may be obtained from your technical service contact on request.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.